

Material Name: Gold Coast Series

Properties:	Typical Values	ASTM Method
Tensile Strength:		
To break: Elongation before break:	5,400 psi 35%	D-638 D-638
Flexural Strength:		
Loan to stretch outer surface 5%	7,000 psi	D-790
Gravity:	1.15	D-792
Rockwell Hardness:	R99, L77	D-785
IZOD Impact Strength		
Notched at 73°F (22.777°C) Notched at 32°F (0°C)	1.2 ft lbs/in .7 ft lbs/in	D-256 D-256
Deflection Temperature		
Temperature at which material deflects .010" (.254mm) at 264 psi	170°F (53.926°C)	D-648
Coefficient of Thermal Expansion		
Inch/inch/°F	3.8 x 10-5	D-696

Gold Coast Series softens at about 200°F (93.33°C) sufficiently so that it can be drilled, sawed, sheared, nailed, bonded and die-cut.

The base material was tested for flammability by the Underwriters Laboratories. The material is rated 94 HB on the UL 94 test.



P.O. Box 7065 | Algonquin, IL 60142 Fax: 815 477 1210 | email: IPI@mc.net www.inoplas.com